

Resistensoversigt

Nedenstående supplerende testresultater er udarbejdet i overensstemmelse med EN 374. Alle test er foretaget efter år 2005.

INDEX for GENNEMBRUDSTID

> 10 min. =	<input type="checkbox"/> 1	> 30 min. =	<input type="checkbox"/> 2	> 60 min. =	<input type="checkbox"/> 3
> 120 min. =	<input type="checkbox"/> 4	> 240 min. =	<input type="checkbox"/> 5	> 480 min. =	<input type="checkbox"/> 6

Eural G2N Sensiderm

CAS nr.	Kemikalie	
64-19-7	1-Butanol	2
108-24-7	1-Pentanol	2
67-64-1	1-Propanol	1
75-05-08	2-Butanol	2
107-13-01	Acetone	0
628-63-7	Acetonitril	0
71-36-3	Acrylonitril	0
78-92-2	Butoxyethanol	0
123-86-4	Butylacetat	0
56-23-5	Chlorbenzen	0
108-90-7	Citronsyre 25%	6
77-92-9	Cyclohexan	1
98-82-8	Cyclohexanol	3
110-82-7	Cyclohexanon	0
108-93-0	Cyclohexylamin	1
108-94-1	D-Limonene	1
108-91-8	Diacetonalkohol	1
123-42-2	Eddikesyre 50%	3
60-00-4	Eddikesyreanhydrid 97%	0
64-17-5	EDTA-4Na 40%	6
107-15-3	Ethanol	1
111-76-2	Ethoxyethanol	0
110-80-5	Ethoxyethylacetat	0
111-15-9	Ethylendiamin	0
111-30-8	Glutaraldehyd	6
79-14-1	Heptaner	0
142-82-5	Hexane	0
10-82-5	Hydroxyeddikesyre 70%	6
7647-01-0	Hypochlorit 10%	6
7647-01-0	Iso Butylalkohol	1
78-83-1	Iso Octane	3
540-84-1	Iso Pentylacetat	0
123-92-2	Isopropanol	2
67-63-0	Kaliumhydroxid 50%	6
8008-20-6	Maleinsyre 40%	6
50-21-5	Methanol	0



CAS nr.	Kemikalie	
5989-27-5	Methylpyrrolydon	-
110-16-7	Mælkesyre 85%	6
67-56-1	N-Octane	0
872-50-4	Natriumhydroxid 5%	6
7697-37-2	Natriumhydroxid 50%	6
7697-37-2	Natriumlaurylsulfat 25%	6
7697-37-2	Octylalkohol	6
111-65-9	Pentaner	0
111-87-5	Pentylacetat	0
109-66-0	Petroleum	6
71-41-0	Phosphorsyre 85%	6
7664-38-2	Propylbenzener	0
1310-58-3	Salpetersyre 16%	6
71-23-8	Salpetersyre 35%	6
151-21-3	Salpetersyre 70%	2
7681-52-9	Saltsyre 10%	6
1310-73-2	Saltsyre 36%	6
1310-73-2	Svovlsyre 50%	6
7664-93-9	Svovlsyre 96%	4
7664-93-9	Tetrachlormethan	0